



HEAT TRANSFER VINYL PRESS SETTINGS

SETTINGS MAY VARY DEPENDING ON YOUR MODEL OF HEAT-PRESS DUE TO TEMP/PRESSURE MANAGEMENT. TEST PRESS IS RECOMMENDED

HTV	TIME TEMP	PRESSURE PEEL
ECONOV	8-10 SECONDS 300°F	34 PSI +/- 2 HOT/WARM PEEL
ECONOMETAL	10 SECONDS 300°F	34 PSI +/- 2 COOL PEEL
ECONOHOLO	10 SECONDS 300°F	34 PSI +/- 2 COOL PEEL
ECONOREFLECT	10 SECONDS 300°F	34 PSI +/- 2 WARM/HOT PEEL
ECONOFLOCK	10 SECONDS 300°F	34 PSI +/- 2 WARM PEEL
ECONOGLITTER	10 SECONDS 300°F	34 PSI +/- 2 WARM PEEL
ECONOPUFF	8-12 SECONDS 300°F	38 PSI +2 HOT PEEL
ECONOCARBON	10 SECONDS 300°F	34 PSI +/- 2 WARM PEEL
ECONOFLEX	8-10 SECONDS 300°F	34 PSI +/- 2 HOT/WARM PEEL
ECONOSENSITIVE (LIGHT/HEAT)	10 SECONDS 300°F	34 PSI +/- 2 WARM PEEL



HEAT TRANSFER VINYL PRESS SETTINGS

SETTINGS MAY VARY DEPENDING ON YOUR MODEL OF HEAT-PRESS DUE TO TEMP./PRESSURE MANAGEMENT. TEST PRESS IS RECOMMENDED

HTV	TIME TEMP	PRESSURE PEEL
ECONOGLOW	10 SECONDS 300°F	34 PSI +/- 2 WARM PEEL
ECONOHAIRLINE	10 SECONDS 300°F	34 PSI +/- 2 WARM PEEL
ECONOBRICK	8-12 SECONDS 300°F <small>**IF POSSIBLE, APPLY A FINAL PRESS ON THE BACK OF THE GARMENT (8 SECONDS)**</small>	34 PSI +/- 2 WARM PEEL
ECONOCHAMELEON	10 SECONDS 300°F	34 PSI +/- 2 WARM PEEL
ECONOSTRETCH	10 SECONDS 300°F	34 PSI +/- 2 HOT PEEL [®]
ECONOSUB FLOCK	10-12 SECONDS 300°F	34 PSI +/- 2 WARM PEEL
ECONOSUB FABRIC	10-12 SECONDS 300°F	34 PSI +/- 2 WARM PEEL
ECONOPRINT	10-12 SECONDS 300°F	34 PSI +/- 2 WARM PEEL
(WHITE/CLEAR/SILVER) ECONOPRINT INK JET	20 SECONDS 300-320°F	34 PSI +/- 2 WARM PEEL
ECONOSUB VINYL	10-15 SECONDS 320°F	34 PSI +/- 2 WARM PEEL



HEAT TRANSFER VINYL PRESS SETTINGS

****SETTINGS MAY VARY DEPENDING ON YOUR MODEL OF HEAT-PRESS DUE TO TEMP./PRESSURE MANAGEMENT. TEST PRESS IS RECOMMENDED****

HTV

ECONOVENT

TIME | TEMP

10 SECONDS 300°F

PRESSURE | PEEL

34 PSI +/- 2 HOT PEEL

